

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 63-299093

(43)Date of publication of application : 06.12.1988

(51)Int.Cl.

H05B 33/14  
H05B 33/20

(21)Application number : 62-131750

(71)Applicant : RICOH CO LTD

(22)Date of filing : 29.05.1987

(72)Inventor : KAGEYAMA YOSHIYUKI

OSETO SEIICHI

KAMEYAMA KENJI


DEGUCHI KOJI

## (54) ELECTROLUMINESCENCE ELEMENT

### (57)Abstract:

**PURPOSE:** To obtain an electroluminescence element with little aging deterioration of luminance and excellent in long-term reliability by forming the side of an insulating layer in contact with a luminescent layer with a fluoride of an alkaline earth element which is a constituting element of the luminescent layer.

**CONSTITUTION:** In an electroluminescence element provided with a transparent electrode 2, an insulating layer 3, and a luminescent layer 4 on a substrate 1, the luminescent layer 4 is formed with a alkaline earth chalcogenide as a base material, and the side of the insulating layer at least in contact with the luminescent layer 3 is formed with a fluoride of an alkaline earth element which is a constituting element of the luminescent layer 4. These alkaline earth fluoride insulating layers are formed by thin film forming methods such as sputtering, ion plating, EB deposition, MOCVD. A stable electroluminescence element with little aging change of the luminescent luminance can be thereby obtained.



## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office